



TEST REPORT

100 Clemson Research Blvd.
Anderson, SC 29625
(864) 656-1094
Fax: (864) 656-1095
www.brickandtile.org

Results of Tests on brick Conducted in accordance with ASTM C 67-16 Standard Test Methods for Sampling and

Testing Brick and Structural Clay Tile

10/18/2017

Name:	Kansas Brick & Tile 767 U.S. 281 Hoisington , KS 67544	Plant:	Kansas Brick & Tile	*Temperature: 60 - 90F
Phone:	620-653-2157	Report Number:	7830-17495	*Humidity: 30% - 70%
Fax:		Received Date:	09/26/2017	
		Sampled Date:	09/26/2017	
		Lot:		
		Product Code:		

Sample Description: **530 Dark, 500 Mahogany, 500 Chestnut, 500 Charcoal, Red Rock, Twilight, 530 MM, 730 S, Delaware, 910 C1**

							Test Date
Absorption	1	2	3	4	5	Average	
24 Hour Submersion in Cold Water (%)	3.67	4.01	3.46	3.96	4.11	3.84	10/03/2017
5 Hour Submersion in Boiling Water (%)	6.44	6.70	6.26	6.77	6.77	6.59	
Saturation Coefficient (Ratio of 24H to 5H)	0.57	0.60	0.55	0.59	0.61	0.58	
 Compressive Strength	1	2	3	4	5	Average	
psi	12,152	13,877	13,610	12,425	13,867	13,186	09/28/2017
MPa	83.8	95.7	93.8	85.7	95.6	90.9	
 Efflorescence	11	12	13	14	15		
Not Effloresced	Not Effloresced	Not Effloresced	Not Effloresced	Not Effloresced	Not Effloresced		10/09/2017
 IRA (Oven Dried Method)	6	7	8	9	10	Average	
g/min/30 in. ²	10.2	4.7	5.4	6.3	6.8	6.7	09/29/2017
 Average % Void	23.3						09/28/2017

The brick represented by the test results shown here comply with the physical property requirements of the standards listed below:

ASTM C 216 - 17 Standard Specification for Facing Brick (Solid Masonry Units Made From Clay or Shale)

Grade: SW, MW

Michael Walker, Quality Manager

**The temperature and humidity of the Bishop Materials Laboratory is constantly kept between 60 -90F, and 30-70% RH*

The results shown above apply only to the samples tested, which are provided by the customer.

This test report shall not be reproduced except in full, without written approval of the laboratory.